

## □ySpecification□z

### □yTitle□z

Method for compacting reduced fine ore in a plate form and method for manufacturing compaction fir melter gasifier using compacted fine iron ore.

### □yBrief description of the drawings□z

FIG. 1 is a conceptional view of a process for manufacturing molten iron including an embodiment of an apparatus for manufacturing hot compacted materials; a fluidized-bed reduction reactor for reducing fine iron ores; and a melter-gasifier for producing molten iron and slag by charging raw coals and reduced irons thereinto to realize the present invention.

FIG. 2 is a detailed view of an entire process of the apparatus for manufacturing hot compacted materials including a hot storage installation for storing fine reduced irons and calcined additives; an apparatus for charging fine reduced irons; and an apparatus for manufacturing hot compacted materials including crusher and so on.

FIG. 3 is a detailed sectional view of a charging bin provided in the apparatus for manufacturing hot compacted materials from the fine reduced irons and calcined additives in order to manufacture compacted materials with a plate form according to the present invention.

FIG. 4 is a structural view of a hot molding part provided in the apparatus for manufacturing hot compacted materials from the fine reduced irons and calcined additives in order to manufacture compacted materials with a plate form according to the present invention wherein a) shows an outer prespective view of the hot molding part and b) shows a detailed sectional view of the press roll.

FIG. 5 is a detailed view of a compacted shape of the fine reduced irons and calcined additives molded by a roll tyre of the press roll provided in the apparatus for manufacturing hot compacted materials from the fine reduced irons and calcined additives in order to manufacture compacted materials with a plate form according to the present invention.

FIG. 6 is a hot molding part and a hot crushing part provided in the apparatus for manufacturing hot compacted materials from the fine reduced irons and calcined additives in order to manufacture compacted materials with a plate form according to the present invention.

FIG. 7 is a perspective view of a crushing roll including a hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention.

FIG. 8 is a detailed view of a hot branching part provided in the hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention wherein a) shows a left sectional view and b) shows a right sectional view.

FIG. 9 is a detailed view of an apparatus for cooling and transferring compacted materials provided in the hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention.

FIG. 10 is a longitudinal sectional view of a hot separation part provided in the hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention.

FIG. 11 is a horizontal sectional view of a second crushing part provided in a hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention.

FIG. 12 is a horizontal sectional view of a structure of the second crushing part provided in a hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention.

FIG. 13 is a longitudinal sectional view of a structure of the second crushing part provided in a hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention.

FIG. 14 is a detailed view of a hot transferring part provided in a hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention wherein a) is a side view and b) is a detailed sectional view.

FIG. 15 is a systematic view of wet scrubber provided in a hot crushing part for crushing compacted materials with a plate form into compacted material for being used in the melter-gasifier according to the present invention.

FIG. 16 is a schematic view of a fluidized-bed reduction reactor for reducing fine iron ores according to a conventional art and a process for manufacturing molten iron including a melter-gasifier manufacturing molten iron and slag by charging raw coals and reduced irons thereinto.

FIG. 17 is a schematic view of conventional press rolls and the compacted materials manufactured by using the press rolls wherein a) shows a press roll and b) shows compacted materials.

FIG. 18 is a schematic view of other conventional press rolls and the compacted materials manufactured by using the press rolls wherein a) shows a press roll and b) shows compacted materials.

FIG. 19 is a schematic view of press rolls and the compacted materials manufactured by using the press rolls in accordance with the present invention wherein a) shows a press roll; b) shows compacted materials pressed by press rolls which are arranged for their grooves to be offset with each other according to the present invention; and c) shows compacted materials pressed by press rolls which are arranged for their grooves to be correspond with each other.

\* explanation of reference numerals of the main part shown in the drawings \*

- 1. apparatus for manufacturing hot compacted materials
- 5. pressured transferring pipe
- 10. hot storage bin
- 12. apparatus for controlling level
- 17. transfer/block valve
- 18a. plate
- 18b. hydraulic actuator
- 20. charging bin
- 26a, 26b. charging device
- 28a, 28b. charging member
- 30a, 30b. electric motor
- 32. hot pressing part
- 36a, 36b. press roll
- 38a, 38b. hydraulic motor
- 40. hydraulic pressing part
- 42a. body shaft
- 42b. roll tyre
- 44. cooling water
- 50. hot crushing part
- 54. crushing plate
- 54a. spacer ring
- 56. protrusion
- 60. hot branching part
- 62. hollow type housing

68. separation plate  
70. hydraulic cylinder  
80. cooling and transferring device  
82. water container  
86, 88. pan conveyor  
90. belt  
95. storage tank  
100. hot separation part  
102. inlet port  
106. casing  
110. spring  
112. vibrator  
115. fine particle outlet port  
120. second hot crushing part  
122. disc type blade  
124. spacer ring  
126. tie bolt  
130a, 130b. cylindric reduced iron scale crushing roll  
134. central axis  
150. hot transferring part  
152. bucket  
154. chain  
156. compacted materials loading part  
158. compacted materials unloading part  
160. fine reduced iron swing motor  
170. tunnel  
180. hot storage part  
190. charging device  
200. wet dust collector  
210. wet scrubber  
212. moisture remover  
300. preheater  
310. pre-reduction reactor  
320. final reduction reactor  
330. fluidized-bed reduction reactor  
340. melter-gasifier

### C. compacted materials

□yDetailed description of the invention□z

□yObject of the invention□z

□yTechnical field to which the invention belongs and background of the technical field□z

<59> The present invention relates to a method for manufacturing compacted materials of fine reduced irons with a plate form, which can be continuously produced with further thickness thereof during manufacturing of molten iron using raw coals and fine iron ores. In addition, the present invention relates to a method for manufacturing compacted materials for being used in a melter-gasifier by using the compacted materials with a plate form.

<60>| <80> omitted

□yTechnical object of the invention□z

<81> In the present invention regarding a process for manufacturing molten iron by using raw coals and fine iron ores, mixture of the hot fine reduced irons and calcined additives or only hot fine reduced irons discharged from a fluidized-bed reduction reactor are pressed under a suitable pressing condition. Therefore, the object of the present invention is to provide a method for manufacturing compacted materials of fine reduced irons with a thick plate form without split or breaking which can minimize an amount of dusts.

<82> Another object of the present invention is to provide compacted materials for being used in the melter-gasifier with a strength, density and size distribution thereof suitable for being melted and slagging in the melter-gasifier by roll pressing and crushing fine reduced irons under a suitable pressing condition.

□yConstitution of the invention□z

<83> The present invention will be explained as follows.

<84> The present invention relates to a method for manufacturing compacted materials of fine reduced irons with a plate form, which can be continuously produced with further thickness thereof during manufacturing of molten iron using raw coals and fine iron ores. In addition, the present invention relates to a method for manufacturing compacted materials for being used in a melter-gasifier by using the compacted materials with a plate form comprising

<85> a step of arranging grooves of the left and right press rolls with a suitable gap therebetween to be offset with each other. A surface of the left and right press rolls includes flat portions and the grooves; and

<86> a step of manufacturing compacted materials with a plate form by charging and pressing mixture of the hot fine reduced irons and calcined additives or only hot fine reduced irons discharged from a final reduction reactor of fluidized-bed reduction reactors into a gap formed between the left and right press rolls while rotating them along a direction opposing to each other, thereby manufacturing the compacted materials with a plate form are provided.

<87> In addition, a method for manufacturing compacted materials for being used in a melter-gasifier in a process for manufacturing molten iron by using raw coals and fine iron ores in an apparatus for manufacturing molten iron including multi-staged fluidized-bed reduction reactors for reducing the fine ores; and a packed type melter-gasifier for manufacturing molten iron by using the fine reduced irons comprising

<88> a step of arranging grooves of the left and right press rolls with a suitable gap therebetween to be offset with each other, a surface of the left and right press rolls comprising flat portions and the grooves;

<89> a step of manufacturing compacted materials with a plate form by charging and pressing mixture of the hot fine reduced irons and calcined additives or only hot fine reduced irons discharged from a final reduction reactor of the fluidized-bed reduction reactors into a gap formed between the left and right press rolls while rotating them along a direction opposing to each other, thereby manufacturing the compacted materials with a plate form; and

<90> a step of crushing the manufactured compacted materials in order to have a shape and mechanical property which are suitable for being charged into the melter-gasifier.

<91> The present invention will be explained in detail as follows.

<92> The present invention is preferably applied to a process for manufacturing molten iron by using raw coals and fine iron ores in an apparatus for manufacturing molten iron including multi-staged fluidized-bed reduction reactors for reducing the fine ores; and a packed type melter-gasifier for manufacturing molten iron by using the fine reduced irons.

<93> According to the present invention, the grooves of the left and right press rolls are arranged to have a suitable gap therebetween to be offset with each other in order to manufacture compacted materials with a plate form. A surface of the left and right press rolls includes flat portions and the grooves.

<94> It is preferable that each flat portion of a surface of the left and right press rolls is formed to have a length of a range from 1mm to 5mm along a direction parallel to a rotating direction of the press rolls; and the a depth of the groove of the surface of the

press roll is in a range from 3mm to 15mm and a distance between the grooves is in a range from 20mm to 50mm.

<95> In addition, it is preferable that a section breaking the groove along a direction to be horizontal to a rotating direction of the roll has a rounded arc shape and has a line shape along a direction to be perpendicular to a rotating direction of the roll.

<96> The offset distance between the left and right press rolls is preferably in a range from 50% to 70% of the distance between the grooves.

<97> As described above, after the the left and right press rolls are arranged, mixture of the hot fine reduced irons and calcined additives or only hot fine reduced irons discharged from a final reduction reactor of the fluidized-bed reduction reactors are charged and pressed into a gap formed between the left and right press rolls while rotating them along a direction opposing to each other, thereby manufacturing the compacted materials with a plate form are manufactured.

<98> As a material manufactured into a compacted material with a plate form can be hot fine reduced irons or mixture of the hot fine reduced irons and calcined additives.

<99> As an example of using hot fine reduced irons as a material manufactured into compacted materials with a plate shape can be those discharged from a final reduction reactor of the fluidized-bed reduction reactors afte the fine iron ores are charged into the multi-staged fluidized-bed reduction reactors.

<100> In addition, an example of using the mixture of the hot fine reduced irons and calcined additives as compacted material with a plate form can be those discharged from a final reduction reactor of the fluidized-bed reduction reactors afte the fine iron ores and additives are charged into the multi-staged fluidized-bed reduction reactors

<101> An amount of the calcined additives in the mixture of the hot fine reduced irons and calcined additives is preferably in a range from 3wt% to 20wt% of the total amount of the compacted materials.

<102> The calcined aditives play a role to prevent the fine reduced irons from sticking to the press roll. However, the amount thereof is too less, it is impossible to expect the above role thereof and combination property of the compacted materials is deteriorated since an amount of the fine reduced irons playing a role to render a sticking property if the amount thereof is too much. Therefore, an amount of the calcined additives is preferably limited in a range from 3wt% to 20wt% of the total amount of the compacted materials.

<103> The pressing temperature is preferably set to be in a range from 400;æ to 800;æ. The reasons are as follows. A sticking property of the comapcted material is deteriorated if the pressing temperature is too low. The fine reduced iron can be stick

to a surface of the press roll if the pressing temperature is too high.

<104> The pressing pressure is preferably set to be in a range from 140bar to 250bar during the roll pressing. The reasons are as follows. The density thereof not only becomes too high but also it is not necessary to consume such energy if the pressing pressure is too high. The strength thereof is further reduced and then particles are severely generated if the pressing pressure is too low.

<105> A pressing condition is preferably set to make a density of the compacted material be in a range from 3.5ton/m<sup>3</sup> to 4.2ton/m<sup>3</sup> and make a thickness thereof be in a range from 3mm to 30mm when the compacted material is pressed according to the present invention.

<106> The compacted materials with a plate form manufactured like above are crushed to have a shape and mechanical property which are suitable for being charged into the melter-gasifier in order to manufacture compacted materials according to the present invention.

<107> The compacted materials manufactured like above have an irregular shape with a density of a range from 3.5ton/m<sup>3</sup> to 4.2ton/m<sup>3</sup> and a size not more than 50mm, preferably 30mm.

<108> More preferably, a size distribution of the compacted materials for being used in the melter-gasifier is not more than 20% with a size of a range from 30mm to 50mm; at a range from 10% to 40% with a size of a range from 30mm to 50mm; at a range from 10% to 40% with a size of a range from 10mm to 20mm; at a range from 5% to 30% with a size of a range from 1mm to 10mm; and at a range not more than 10% with a size of not more than 1mm.

<109> The present invention will be explained in detail with reference to FIGs. 1 to 15.

<110> First, the apparatus for manufacturing compacted materials, which corresponds with the present invention, for compacting hot fine reduced irons and calcined additives; and then manufacturing compacted materials are explained.

<111> An embodiment of the apparatus for manufacturing hot compacted materials for compacting hot fine reduced irons and calcined additives is shown in FIGs. 1 to 5.

<112> As shown in FIG. 1, the apparatus for manufacturing hot compacted materials 1 is located between the final reduction reactor 320 and the melter-gasifier 340.

<113>...<117> omitted

<118> As shown in FIG. 3, in the hot charging devices 26a and 26b, two sets of spiral type charging members 28a and 28b are slanted at both sides of the charging bin 20 to a direction to be perpendicular direction and arranged toward a lower end outlet port of the charging bin 20. The electric motors 30a and 30b are provided to rotate and fine

reduced iron over the charging members 28a and 28b at an upper end of the charging bin 20.

<119> The spiral type charging members 28a and 28b are installed above the left and right press rolls 36a and 36b, which will be explained below, and make a charging amount of the fine reduced iron be the same as that of the calcined additives.

<120>, <121> omitted

<122> A hot press roll 32, which presses the fine reduced iron and calcined additives into a plate form, is connected to the lower end of the charging bin 20.

<123>, <124> omitted

<125> In addition, the press rolls 36a and 36b are sequentially arranged at a lower portion of the charging members 28a and 28b and thereby pressing the fine reduced iron and calcined additives into a plate form while being rotated along a direction opposing to each other.

<126>...<129> omitted

<130> In addition, as shown in FIG. 5, the surface of the roll tyre 42b consists of a flat portion and a groove which are alternately formed to be located.

<131> The left press roll 36a and the right press roll 36b are arranged to have a suitable gap therebetween. In addition, the groove formed on a surface of the roll tyre 42b of the left press roll 36a is arranged to be offset with the groove formed on a surface of the roll tyre 42b of the right press roll 36b.

<132> Each flat portion of a surface of the roll tyre 42b of the left and right press rolls 36a and 36b is preferably formed to have a length of a range from 1mm to 5mm along a direction parallel to a rotating direction of the press rolls. In addition, a depth of the groove of the surface of the press roll is preferably in a range from 3mm to 15mm and a distance between the grooves is preferably in a range from 20mm to 50mm.

<133> The offset distance between the left and right press rolls is preferably in a range from 50% to 70% of the distance between the grooves.

<134> By forming and arranging the press roll like above, the sheet of the compacted materials suitable for being crushed in the hot crushing part 50, which will be explained below, is formed.

<135> omitted

<136> When the hot press roll 32 presses the fine reduced iron and calcined additives, pressed compacted materials with a plate form is manufactured.

<137> omitted

<138> A crushing device for crushing the manufactured compacted materials according to the present invention in order to have a shape and mechanical property

which are suitable for being charged into the melter-gasifier will be explained.

<139> As shown in FIG. 6, a hot crushing part 50 is located under the hot press roll 32 sequentially connected thereto. The hot crushing part 50 separates and crushes the fine reduced irons and calcined additives C with a plate form to have a size suitable for being charged into the melter-gasifier 340.

<140> The hot crushing part 50 is a device for firstly separating and crushing the compacted materials C made of the fine reduced irons and calcined additives pressed by the hot press roll 32 as a size suitable for being charged into the melter-gasifier 340.

<141>...<154> omitted

<155> Meanwhile, a hot separation part 100 is provided to sequentially connect with the discharging port 66b of the hot branching part 60 and separate large grains contained in the firstly crushed hot compacted materials made of the fine reduced irons and calcined additives.

<156> The hot separation part 100 is connected to the hot crushing part 7 and separates compacted materials C made of the fine reduced irons and calcined additives with a size of not less than 50mm, preferably not less than 30mm after the compacted materials C are crushed. The hot separation part 100 can separate the compacted materials C at a maximum rate of 120ton/h. As shown in FIG. 10, the hot separation part 100 separates a grain with a size of not less than 50mm, preferably not less than 30mm by vibrating the compacted materials C made of the fine reduced irons and calcined additives charged through an inlet port 102 of the upper portion. The inlet port 102 is formed at an upper portion of a casing 106 including a slanted screen 104 and a large grain discharging port 108 is formed at an opposing side of the inlet port 102.

<157> omitted

<158> Therefore, such hot separation part 100 discharges the compacted materials C with a size of not less than 50mm, preferably not less than 30mm through the large grain discharging port 108 and discharges the rest compacted materials C with a small size through the small grain discharging port 115. In addition, a second hot crushing part 120, which will be explained below, is arranged under the large grain discharging port 108. A hot transferring part 150 is connected to a lower portion of the small grain discharging port 115 in order to transfer the crushed hot compacted materials C made of the fine reduced irons and calcined additives.

<159> As entirely shown in FIG. 11, the second hot crushing part 120, which is connected to the large grain discharging port 108, is sequentially connected to the hot separation part 100. The second hot crushing part 120 separates and crushes the

separated compacted materials C made of fine reduced irons and calcined additives with a large grain size to be suitable for being charged into the melter-gasifier 340.

<160>...<165> omitted

<166> The second hot crushing part 100, which is connected to the large grain discharging outlet 108 of the hot separation part 100, crushes compacted materials C made of the fine reduced irons and calcined additives with a size over 50mm, preferably over 30mm suitable for being charged into the melter-gasifier 340. The second hot crushing part 100 can crush the compacted materials C at a maximum rate of 60ton/h. It is possible to variably control a rotating times and a gap between the impact blades 122 in order to minimize the amount of the fine particles generated during crushing of compacted materials C made of the fine reduced irons and calcined additives.

<167>...<175> omitted

<176> In addition, wet dust collector 200 is installed to collect hot dusts generated in a process of transferring, charging, crushing and separating of the compacted materials C made of the fine reduced irons and calcined additives in the apparatus for manufacturing hot compacted materials 1 according to the present invention.

<177> As shown in FIG. 15, dust collectors (not shown) are installed in each of the hot press part 32, a hot crushing part 50, a cooling and transferring device 80, a hot separation part 100, a second hot crushing part 120, a hot transferring part 150 and so on. They are connected to a wet scrubber 210 and a moisture remover 212 through a pipe, thereby discharging residues through a chimney 214 after the dusts are removed.

<178> Constitution, function and effect of the wet dust collector can be easily understood by the skilled art, detailed description thereof is omitted.

<179> A method for manufacturing compacted materials made of fine reduced irons and calcined additives with a plate form by using the apparatus for manufacturing hot compacted materials as shown in FIGs. 1 to 5 and a method for crushing the compacted materials with a plate form by using the crusher as shown in FIGs. 6 and 7 are explained below.

<180>...<185> omitted

<186> As shown in FIG. 5, compacted materials C made of fine reduced irons and calcined additives with a plate shape corresponding to the present invention manufactured by rotating a pair of press rolls, namely the left and right press rolls 36a and 36b with a suitable gap therebetween along a direction opposing to each other by using hydraulic motors 3a and 38b while arranging the groove formed on a surface of the roll tyre 42b of the left press roll 36a and the groove formed on a surface of the roll

tyre 42b of the right press roll 36b to be offset.

<187> It is preferable that each flat portion of a surface of the left and right press rolls is formed to have a length of a range from 1mm to 5mm along a direction parallel to a rotating direction of the press rolls; and the a depth of the groove of the surface of the press roll is in a range from 3mm to 15mm and a distance between the grooves is in a range from 20mm to 50mm.

<188> The offset distance between the left and right press rolls is preferably in a range from 50% to 70% of the distance between the grooves.

<189> An amount of the calcined additives in the mixture of the hot fine reduced irons and calcined additives is preferably in a range from 3wt% to 20wt% of the total amount of the compacted materials.

<190> The pressing temperature is preferably set to be in a range from 400°C to 800°C. The pressing pressure is preferably set to be in a range from 140bar to 250bar during the roll pressing.

<191> A density of the compacted material C made of fine reduced irons and calcined additives is in a range from 3.5ton/m<sup>3</sup> to 4.2ton/m<sup>3</sup> and a thickness thereof is in a range from 3mm to 30mm according to the present invention.

<192> omitted

<193> In the present invention, Compacted materials are pressed by forming grooves on a surface of the roll tyre 42b of the press rolls 36a and 36b and arranging the groove formed on a surface of the roll tyre 42b of the left press roll 36a and the groove formed on a surface of the roll tyre 42b of the right press roll 36b to be offset, thereby a problem of a split of the plate type compacted materials with a thickness over 8mm does not happen.

<194>...<196> omitted

<197> The compacted materials for being used in the melter-gasifier manufactured like above have an irregular shape with a density of a range from 3.5ton/m<sup>3</sup> to 4.2ton/m<sup>3</sup> and a size not more than 50mm, preferably 30mm.

<198> More preferably, a size distribution of the compacted materials for being used in the melter-gasifier is not more than 20% with a size of a range from 30mm to 50mm; at a range from 10% to 40% with a size of a range from 30mm to 50mm; at a range from 10% to 40% with a size of a range from 10mm to 20mm; at a range from 5% to 30% with a size of a range from 1mm to 10mm; and at a range not more than 10% with a size of not more than 1mm.

<199> Meanwhile, an amount of generated fine particles is increased

<202>, <203> omitted

<204> The hot separation part 100 separates a grain with a size of not less than 50mm, preferably not less than 30mm. The grain with a size of not less than 50mm, preferably not less than 30mm is discharged through a large grain discharging outlet port 108 while grain with a size of not more than 50mm, preferably not more than 30mm is discharged through a small grain discharging outlet port 115.

<205> In addition, hot compacted materials for being used in a melter-gasifier with a size of not less than 50mm, preferably not less than 30mm discharged from the large grain discharging outlet port 108 have gone through the a couple of cylindric reduced iron scale crushing rolls 130a and 130b which rotate by the hydraulic motors 132 of the second hot crushing part 120 and then are crushed into a size thereof not more than 50mm, preferably not more than 30mm. and are capable of being charged into the melter-gasifier 340.

<206> In addition, hot compacted materials for being used in a melter-gasifier crushed with a size of not more than 50mm, preferably not more than 30mm, which have gone through the second hot crushing part 120, and the hot compacted materials for being used in a melter-gasifier crushed with a size of not more than 50mm, preferably not more than 30mm, which have gone through a small grain discharging outlet 115 of the hot separation part 100 are loaded into a plurality of buckets 152 of the hot transferring part 150. The buckets 152 are transferred upward by the plurality of chains fine reduced iron screw by an operation of the fine reduced iron screw motor 160 provided in the compact materials unloading part 158 located at an upper side.

<207> In addition, hot compacted materials for being used in a melter-gasifier crushed with a size of not more than 50mm, preferably not more than 30mm, which is transferred by the hot transferring part 150 are loaded into the hot storage bin 180 and then are charged into the melter-gasifier 340 through a plurality of hot pressure equalizing containers 192 and 194 of the charging device 190.

<208> omitted

<209> The dusts of the compacted materials made of fine reduced iron and calcined additives are collected through dust collectors (not shown) are installed in each of the hot press part 32, a hot crushing part 50, a cooling and transferring device 80, a hot separation part 100, a second hot crushing part 120, a hot transferring part 150 and so on. The dusts pass through a wet scrubber 210 and a moisture remover 212 by using a pipe, thereby residues are discharged through a chimney 214 after the dusts are removed.

<210> The present invention is specifically explained with reference to the embodiment below.

<211> Embodiments

<212> The compacted materials with a plate form are manufactured by using a roll press with a surface shape shown in FIGs. 17(a)(flat roll), 18(a)(roll with a groove) and 19(a)(roll of the present invention) by using fine reduced irons and calcined additives of 750 $\mu$ m discharged from the final reduction reactor of the fluidized-bed reduction reactor.

<213> The compacted materials with a flat form manufactured by each of the rolls are shown in FIGs. 17(b), 18(b), 19(b) and 19(c).

<214> FIG. 19(b) shows compacted materials with a flat form manufactured by arranging a pair of press rolls to make their grooves to be offset and FIG. 19(c) shows compacted materials with a flat form manufactured by arranging a pair of press rolls to make their grooves to correspond with each other.

<215> A thickness, a density, productivity and dust generating rate of the compacted materials manufactured by using each of the press roll are investigated and a result thereof is shown in Table 1 below.

<216> Table 1

	flat roll (FIG. 17a)	roll with a groove (FIG. 18a)	roll of the present invention (FIG. 19b) (the grooves are arranged to be offset)
Thickness (mm)	8	10	16
Density (g/cm <sup>3</sup> )	3.8	3.8	3.8
Productivity (%)	100	120	200
Dust generating rate (-1mm, wt%)	10	8	5

<217> As described in Table 1, productivity is increased and dust generating rate is known to be reduced below 5% since the flat type compacted materials with a thickness of 16mm can be manufactured when compacted materials with a flat form

are manufactured according to the present invention.

<218> Especially, when the press rolls are arranged by making their grooves to correspond with each other, split and breaking phenomenon are severely appeared as shown in FIG. 19(c).

<219> In addition, the split phenomenon was severely happened due to an increase of sticking property between the fine reduced irons and the roll when the press rolls with grooves were used.

□yEffect of the invention□z

<220> As described above, the present invention can manufacture thick plate type compacted materials made of fine reduced irons with a minimized generating amount of dusts without split and breaking in a process for manufacturing molten iron by using raw coals and fine iron ores, thereby productivity and effectivity of a process for manufacturing molten iron can be improved.

<221> In addition, the present invention provides compacted materials for being used in the melter-gasifier with a strength, density and size distribution thereof suitable for being melted and slagging in the melter-gasifier, thereby having an effect that improved productivity and effectivity of a process for manufacturing molten iron are promoted.